

# Solar View



## Technical Data

<b>Composition</b>	30% polyester / 70% PVC
<b>Width</b>	3,000mm & 2,500mm
<b>Weight</b>	530gsm +/-5%
<b>Thickness</b>	0.75mm +/-5%
<b>Opacity/Openness</b>	≥ 6
<b>Light Fastness</b>	≥ 5 (Blue wool scale)
<b>Coating</b>	Polyester yarns with PVC coating
<b>Flame Retardant</b>	Product is designed and manufactured to comply with Building Code of Australia requirements for class 2 to 9 buildings
<b>Cleaning</b>	Wipe clean with warm soapy water and damp cloth

**5 YEAR WARRANTY**

**SCREEN**

**ECO FRIENDLY**

**FLAME RETARDANT**

**FR**

## Solar Properties

USA Standard Tested To Ashrae 74-73									
	Ts	Rs	As	Tv/ Vlt	Tuv	O-F	Shading Coefficients (Sc)		
							3mm CL.	6mm CL.	9mm CL.
White	22	64	14	7	21	7	0.36	0.36	0.33
Alabaster	20	61	19	6	19	6	0.38	0.38	0.34
Off White	21	63	16	6	21	7	0.37	0.37	0.34
Cotton	18	61	21	6	18	6	0.37	0.37	0.34
Bone / Off White	17	57	26	6	17	6	0.40	0.40	0.35
Taupe	12	41	47	7	13	7	0.50	0.50	0.40
Grey	12	30	58	7	14	7	0.58	0.58	0.43
Charcoal	6	5	89	6	10	6	0.73	0.73	0.51
Bronze / Charcoal	6	7	87	6	9	6	0.72	0.72	0.50
Black / Copper	7	8	85	7	11	7	0.71	0.71	0.50
Black	7	4	89	6	10	6	0.74	0.74	0.51
Platinum	7	10	83	11	7	7	0.72	0.68	0.50

**Ts** Solar Transmittance    **As** Solar Absorbance    **Tv** Visual Light Transmission    **G-Value** % Solar Radiation through Fabric  
**Rs** Solar Reflection    **Tuv** Ultraviolet Transmittance    **O-F** Openness Factor    **G-Total** % Solar Radiation through Blind and Window

**Melbourne Head Office**  
 Building 1, Level 2, 630 Mitcham Road  
 Mitcham VIC 3132 Australia

P +61 3 9729 9970  
 E [sales@texstyle.com.au](mailto:sales@texstyle.com.au)

Learn more at  
[texstyle.com.au](http://texstyle.com.au)

