



Technical Data Sheet

GrandOak Monarch Collection



General Information

Size	2200mm x 220mm	
Thickness	20mm	
Gloss Level	Matte Finish & Wire Brushed	
Top Layer (Veneer)	6mm European Oak	
Surface Coating	UV Lacquer 8-10 Lacquer Coats	
Origin of Timber Veneer	Europe	
Janka hardness rating	1360 LBF (7.0)	
Profile	Engineered Tongue & Groove	
Pattern	Single Strip	
Structure	8 layer multi-ply core, timber surface veneer	
Edging	Bevelled Edging	
Pack Coverage	1.936m ²	
Pack Weight	29kg	
Pack Length	2200mm, Nested boards in packs*	
Pallet Packs	55	
Application	Residential & Commercial	
Environmental Rating	A+	
Maintenance	As per Australian Select Timbers – GrandOak's care & maintenance instructions - please refer to: asttimbers.com.au/technical/care-maintenance/	



*Nested boards refers that the packs contain both short and full length boards. Minimum length 600mm.

Technical Data Sheet

GrandOak Monarch Collection

Accessories

Matching Colour Stair Nosing	2134 x 90 x 20mm
	(Engineered timber)
Matching Colour Scotia	1900 x 18 x 18mm (Solid timber)
Variable Height Trims	3400 x 22 x 15-20mm (Available in
	Black, Champagne & Silver)

Installation

Fully Bonded	Yes*
Nailed	No
Floated on underlay	Yes*
Over Heated Slab*	Yes*

*Please refer to our Installation Instructions and Heated Slab Instructions for more information on our website.

Grading Specifications

Timber Grade	Classic Allowed Allowed Max 10% width Will be present (Allowed) 40mm diameter (Will be present) Trace	
Colour Variation		
Filled Defects		
Sapwood		
Black Filler		
Maximum size of knots		
Heart/Pith		
End Checks	Filled	
Insect Damage	Filled	
Ingrown Bark	Not Allowed	

GrandOak Monarch Collection is made of European Oak. As a natural timber product, knots will be present, as well as the use of black and/or coloured fillers. Colour variation and grain are to be expected and will also vary on the floorboards. These variations will occur from batch to batch, between samples and the actual stock delivered and installed. These variations are normally present in the GrandOak Monarch Collection and are not considered defects. Furthermore, it will not form the basis of any claims under the warranty.

Filled defects and trace amounts of the heartwood are present in this grade.

This Classic grade of timber is the most common standard and widely used in the timber industry.

Timber flooring is not colour-fast, and the colour will change over time when exposed to UV light. Surface checking may be present.

Installation & Warranty

All GrandOak floors must be installed by a competent approved installer who has all the necessary skills and take individual site circumstance into account. GrandOak's warranty will only apply to floors which have been installed according to the GrandOak's installation instructions available in each pack and also on the GrandOak's website – **grandoakflooring.com.au**

Terms & Conditions: Please note this technical sheet was written by Australian Select Timbers Pty Ltd. All the information is specified correctly while writing and publication of the sheet. The company reserves the right to change the specifications of this product at any time without prior notice to third parties.

Colour Disclaimer: We cannot guarantee that the colours you see printed on this technical data sheet or displayed on our website accurately portrays the true colours of the floorboards. Electrical device's monitors and/or screens are not calibrated equally and colour reproduction on the Internet is not precise. Swatch colours can be verified by ordering a complimentary offcut sample from our website or visiting an Australian Select Timbers' retail partner to view in-store.

Australian Select Timbers Pty Ltd.

Test Results & Certificates[^]

Acoustic Result*	L'nT, w: 45
	(5 Star - AAAC Star Rating)
Legally harvested timber	Yes
FSC	Available upon request
Wet Slip Test	AS 4586:2013 Classification: P3
Dry Slip Test	AS 4586:2013 Classification: D1
Australian Reaction to fire - FLOOR	ASISO 9239.1-2003 Result CRF 5.0 kw/m², smoke value 11%
Australian Reaction to fire - WALL	AS/NZS 3837:1998 Result: 54.1kw/m²
Release of formaldehyde	ASTM D5116 Result 0.011mg/m²/hr (max allowable 0.1)
Release of 4-phenylcyclohexene	ASTM D5116 Result 0.003mg/m²/hr (max allowable 0.05)
Total VOC	ASTM D5116 Result 0.046mg/m²/hr (max allowable 0.5)

^All test reports and certificates are available upon request.

*All testing conducted on 200mm concrete slab and a single layer of 10mm standard suspended plasterboard ceiling (with no insulation) as per B.C.A and AAAC requirements.

Test conducted on site as a floating floor with the use of 2mm and 3mm Select EVA Underlay. Please contact Australian Select Timbers for further information regarding these test results.

Warranties

Warranty - Residential Warranty - Commercial		20 Year Wear & Lifetime Structural 10 Year Wear & Lifetime Structural	