



ROLLER



PANEL

Technical Data

Composition	100% Polyester Trevira CS
Width	2,400mm
Weight	300gsm: Icon, Raven, Shimmer 350gsm: Arctic, Stone, Bronze/Pearl, Beige
Thickness	0.43mm: Icon, Raven, Shimmer 0.48mm: Arctic, Stone, Bronze/Pearl, Beige
Opacity/Openness	Blockout to AS-2663-1999
Light Fastness	5 - 6 Depending on colour. EN ISO 105 – B02
Coating	Blockout coated with acrylic foam
Flame Retardant	AWTA AS1530.3 German Standard DIN 4102 B1 French Standard M1
Cleaning	Surface dust can be removed with vacuum or a soft cloth

5 YEAR WARRANTY

BLOCKOUT

ECO FRIENDLY

FLAME RETARDANT

PVC FREE

FR

trevira CS

ecospecifier

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
Tested for harmful substances.
www.oeko-tex.com/standard100

Solar Properties

USA Standard Tested To Ashrae 74-73

	Ts	Rs	As	Tv/ Vlt	RI	AI	TUV	Shading Coefficients (Sc)		
								3mm CL.	6mm CL.	6mm H.A
Arctic	0	68	32	0	79	21	0	0.32	0.25	0.77
Beige	0	54	46	0	61	39	0	0.40	0.26	0.81
Icon	0	6	94	0	6	94	0	0.68	0.30	0.95
Raven	0	7	93	0	8	92	0	0.67	0.30	0.94
Shimmer	0	14	86	0	16	84	0	0.63	0.30	0.92
Stone	0	15	85	0	15	85	0	0.63	0.30	0.92
Bronze/Pearl	0	30	70	0	34	66	0	0.54	0.28	0.88

Ts Solar Transmittance **As** Solar Absorbance **Tv** Visual Light Transmission **G-Value** % Solar Radiation through Fabric
Rs Solar Reflection **Tuv** Ultraviolet Transmittance **O-F** Openness Factor **G-Total** % Solar Radiation through Blind and Window

Melbourne Head Office

Building 1, Level 2, 630 Mitcham Road
Mitcham VIC 3132 Australia

P +61 3 9729 9970
E sales@texstyle.com.au

Learn more at
texstyle.com.au

